

Synthomer Limited
 Central Road, Templefields,
 Harlow, Essex CM20 2BH
 United Kingdom
 Tel: +44 (0) 1279 436 211
 Fax: +44 (0) 1279 444 025

Synthomer GmbH
 Gwinnerstrasse 19
 D-60388 Frankfurt am Main
 Germany
 Tel: +49 (0) 69 94179 0
 Fax: +49 (0) 69 94179 211



www.synthomer.com

www.synthomer.com

Products for Automotive Interiors

Synthomer	1419**	1480	8580
Applications			
Cabin & boot	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>
Wheelhouse & pillar linings	<input type="radio"/>	<input type="radio"/>	
Reartray, boot & long-board			<input type="radio"/>
Handle:			
stiff	<input type="radio"/>		
very stiff		<input type="radio"/>	<input type="radio"/>
Properties*			
Type	SBc	SBNc	SBc
TSC, %	55,0	53,0	55,0
pH	7,4	7,5	8,5
Butadiene Content, %	20	15	20
Viscosity, mPa·s	250	250	300
Thermomouldable	<input type="radio"/>	<input type="radio"/>	
Main Application			
Frothed backing	<input type="radio"/>	<input type="radio"/>	
Backcoating			<input type="radio"/>
Impregnation	<input type="radio"/>	<input type="radio"/>	<input type="radio"/>

TML_En BDL/REI 11/2003

S = Styrene B = Butadiene N = Acrylonitrile c = carboxylated

Please contact our Technical Service Department for details of other grades available.

* Typical data. For specifications please see certificate.

** Modifications for special production demands are available.

All information is correct at the date of publication and is given in good faith, but without warranty.
 We cannot accept liability for any damage, loss or patent infringement resulting from the use of this information.

Die Angaben entsprechen dem heutigen Stand unserer Kenntnisse. Sie gelten jedoch nur als unverbindliche Hinweise,
 eine Eigenschaftszusicherung ist damit nicht verbunden. Rechte Dritter sind zu beachten.